

NERVÜRLÜ BETON ÇELİĞİ
DEFORMED REINFORCING STEEL BAR
(TS 708/2016)

ÇAP, d mm	KESİT ALANI mm²	BİRİM AĞIRLIK kg/m	AĞIRLIK TOLERANS %
8	50,3	0,395	±6
10	78,5	0,617	
12	113	0,888	
14	154	1,210	
16	201	1,580	
18	154,4	2,000	
20	314	2,470	
22	380	2,985	
24	452,3	3,550	
25	491	3,850	
26	531	4,168	
28	616	4,830	
30	706,5	5,550	
32	804	6,310	